

Polyurethane Foam Specification Sheet

Foam Grade:	1950 MFR (MIL-PRF-26514G Type I, Class II, Grade B)		
TEST OR STANDARD¹		SPECIFICATION	
Density – PCF (pounds per cubic foot)		1.85 ± .05	
IFD on 4" at 25% deflection		40-50	
Resilience - % minimum		40	
Tensile Strength – PSI (lbs./in ²) minimum		12	
Elongation - % minimum		175	
Tear Strength – lb./in., minimum		2.0	
90% Compression Set - % maximum		10.0	
Combustibility:			
MIL-26514G		Pass	

¹ ASTM D-3574-01

LIMITATIONS OR WARRANTIES AND REMEDIES

The above product information is furnished for informational purposes only for the convenience of potential customers. It is not intended to be, nor shall it be construed or interpreted to be, a representation, warranty, or inducement of any kind whatsoever. ADVANCED URETHANE TECHNOLOGIES, DISCLAIMS ANY AND ALL WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTY OF THE MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE. Advanced Urethane Technologies, believes in good faith that the information contained herein is accurate to the best of its knowledge, but Advanced Urethane Technologies, does not assume any legal or other responsibility with respect thereto or for the use or reliance thereon. Upon purchase of any products from Advanced Urethane Technologies, the customer represents the warrants to Advanced Urethane Technologies, that such customer has tested the product for its own use and has determined that the product is suitable for such intended use of which Advanced Urethane Technologies, disclaims any knowledge. IN NO EVENT SHALL ADVANCED URETHANE TECHNOLOGIES, HAVE ANY LIABILITY TO ITS CUSTOMERS OR THE PURCHASE FROM ITS CUSTOMERS FOR ANY COMMERCIAL LOSS, CLAIMS FOR LABOR OR MATERIALS, ANY COST OF COVER, ANY OTHER ORDINARY LOSSES OR GENERAL DIRECT OR INDIRECT DAMAGES, ANY INCIDENTAL SPECIAL OR CONSEQUENTIAL DAMAGES (except compensatory damages for physical injuries to persons or physical tangible property), LOST PROFITS, LOST BUSINESS OPPORTUNITIES OR LOSS OF GOODWILL OR THE LIKE.