



1055 White Mountain Highway Milton, NH 03851
 1-800-662-3626 main 1-603-652-9279 fax
www.indexpackaging.com

Polyurethane Foam Specification Sheet

Foam Grade:	1544
TEST OR STANDARD¹	SPECIFICATION
Density – PCF (pounds per cubic foot)	1.45 ± .05
IFD on 4” at 25% deflection	40-48
Resilience - % minimum	40
Tensile Strength – PSI (lbs./in ²) minimum	15
Elongation - % minimum	125
Tear Strength – lb./in., minimum	2.0
90% Compression Set - % maximum	10.0
Combustibility:	
Pass (Tested upon Request)	TB-117 2013 Sec 3

¹ ASTM D-3574-91

LIMITATIONS OR WARRANTIES AND REMEDIES

The above product information is furnished for informational purposes only for the convenience of potential customers. It is not intended to be, nor shall it be construed or interpreted to be, a representation, warranty, or inducement of any kind whatsoever. INDEX PACKAGING INC, DISCLAIMS ANY AND ALL WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTY OF THE MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE. Index Packaging Inc., believes in good faith that the information contained herein is accurate to the best of its knowledge, but Index Packaging Inc., does not assume any legal or other responsibility with respect thereto or for the use or reliance thereon. Upon purchase of any products from Index Packaging Inc. the customer represents the warrants to Index Packaging Inc., that such customer has tested the product for its own use and has determined that the product is suitable for such intended use of which Index Packaging Inc., disclaims any knowledge. IN NO EVENT SHALL INDEX PACKAGING INC., HAVE ANY LIABILITY TO ITS CUSTOMERS OR THE PURCHASE FROM ITS CUSTOMERS FOR ANY COMMERCIAL LOSS, CLAIMS FOR LABOR OR MATERIALS, ANY COST OF COVER, ANY OTHER ORDINARY LOSSES OR GENERAL DIRECT OR INDIRECT DAMAGES, ANY INCIDENTAL SPECIAL OR CONSEQUENTIAL DAMAGES (except compensatory damages for physical injuries to persons or physical tangible property), LOST PROFITS, LOST BUSINESS OPPORTUNITIES OR LOSS OF GOODWILL OR THE LIKE.